



COURT SECURITY

Single Part Wood Coating

PRODUCT DESCRIPTION & BENEFITS

COURT SECURITY is a single component, oxygen crosslinked, water based, oil modified urethane which provides performance comparable to conventional solvent-based products. In addition, it exhibits all the advantages of water-based products including fast dry, water clean up, low odor and responds well to high speed burnishing.

DETAILED USAGE & INSTRUCTIONS

PREVIOUSLY FINISHED FLOORS: Clean floor with COURT APPOINTED Wood Floor Prep Cleaner following label instructions. Abrade entire floor with 120 grit screens. Use each side of screen for approximately 200 sq. ft. Vacuum and tack with a clean towel and water. Allow floor to dry. Apply two coats of COURT SECURITY. **NEWLY SANDED FLOORS:** Tack floor with COURT APPROVED Waterless Cleaner. Allow to dry. Apply first coat of COURT SECURITY. Allow floor to dry and abrade with 120 grit screen. Vacuum, tack and let dry. Install game lines if required. Apply 2-3 coats of COURT SECURITY. After last coat let dry with good ventilation 48-72 hours before traffic. **PREVIOUSLY FINISHED/NEWLY SANDED FLOORS:** COURT SECURITY should be applied as soon as the final sanding step has been completed. Floor should also be vacuumed and tack ragged with COURT APPOINTED WOOD Floor Prep Cleaner to assure that the surface is dust free. Apply initial coat of COURT SECURITY with grain of the wood at the rate of 600 square feet per gallon. Let dry overnight and abrade with a 120 grit screen. Vacuum and tack. Apply a second coat of seal. Line athletic courts with a solvent resistant oil based paint. Remove tape within 2 to 3 hours after painting. After paint has dried, buff with maroon pad or lightly abrade with a 120 grit screen. Vacuum and tack rag to remove all dust before applying finish. Apply at least 2 coats of any COURT SYSTEM WOOD FINISH. **PRODUCT APPLICATION NOTE:** Do not apply when temperature exceeds 90°F and humidity is 80% or greater. Close doors and windows and turn off air conditioning and/or ventilating fans. Do not apply more than 2 coats of COURT SECURITY per day. Apply COURT SECURITY with lightweight bar with grain of wood. Allow to dry "tack free" before applying next coat. If more than 12-14 hours elapse between coats, abrade surface with 120 grit screen or 3M Maroon Pad and tack before recoating. **MAINTENANCE:** Dust mop frequently with mop treated with COURT AUTHORIZED Water Based Dust Mop Treatment. Do not use a freshly treated mop or retreat a soiled mop. Damp mop weekly or more often if needed with COURT APPOINTED Wood Floor Prep Cleaner. To restore gloss, high speed burnish with at least a 1500 rpm machine and 3M High Speed Burnishing Hair Pad. To assist in enhancing gloss apply RESTORE ORDER High Speed Restorer. **SPECIAL INSTRUCTIONS:** Do not use over water based floor finishes, shellac, lacquer or coatings and seals containing stearates, waxes or silicones. Adhesive marking tapes and decals may cause delaminatives of coating when removed. For professional use only. **RECOMMENDED PAINT:** Use a high quality water based enamel. Test paint for compatibility.

Refer to the product label or contact a Cynamatic Chemical Co. professional for additional usage instructions.

TECHNICAL SPECIFICATIONS

Appearance / Color	Opaque
Odor	Slight Amine
Shelf Life	2 years
Coverage	600 sq. ft./gal.
Solubility in Water	Complete
V.O.C.	193 gm/l
Dry Time	4-8 hours
Viscosity	67 cps max
Leveling	Excellent
Slip Resistance	>0,5
pH5 ± 0.5
Specific Gravity	1.044 ± 0.005
Storage Temperature.....	45-110 °F

FEATURES & BENEFITS

- Environmentally Safe
- No Mixing Required
- Water Cleanup; Non-Combustible
- Excellent Gloss; High Resistance to Scuffing
- Less Discoloration of Wood and Paint
- Restore Gloss with High Speed Burnishing

002427

CYNAMATIC
CHEMICAL COMPANY

1472 Louis Bork Drive
Batavia, IL 60510